

System Reference	Service	Coating System	# of Coats	Typical Dry Film Thickness		Volume Solids	Gloss	Application
				Microns	Mils			
<b>Concrete Flooring</b>								
1-A	Flooring - mild	Amerlock 2/400	2	300 - 450	12 - 18	83	Semi-gloss	Roll or Spray
1-B		Amerlock 2/400	1	150 - 200	6 - 8	83	High Gloss	Roll or Spray
		Amershield	1	125	5	73		
				275 - 325	23 - 29			
1-C		Nu-Klad 128	1	50 - 100	2 - 4	35	High Gloss	Roll Pour and spread
		Nu-Klad 126	1	250 - 500	10 - 20	100		
			300 - 600	12 - 24				
2-A	Flooring - moderate	Nu-Klad 127	1	150 - 250	6 - 10	100	High Gloss	Pour and spread
2-B		Nu-Klas 126	1	500 - 750	20 - 30	100		
				650 - 1000	26 - 40			
2-B		Nu-Klad 127	1	150 - 250	6 - 10	100	High Gloss	Pour and spread Roll or Spray
		Nu-Klas 126	1	500 - 750	20 - 30	100		
		Nu-Klad Amershield	1	125	5	73		
			775 - 1125	31 - 45				
3-A	Flooring - decorative	Nu-Klad 127	1	150 - 250	6 - 10	100	High Gloss	Pour and spread Broadcast Pour and spread
3-A		Nu-Klas 126	1	250	10	100		
		840 Quartz or 841 Vinyl Flake Additives	NA		NA			
		Nu-Klad 126 Clear	1-2	75 - 150	3 - 6	100		
			475 - 650	19 - 26				
4-A	Flooring - severe	Amerlock Sealer	1	25 - 50	1 - 2	100	Semi-gloss	Spray / Roll Pour and spread
4-A		Nu-Klad 120A	1	1 mm - 4.375 mm	40 - 175	100		
				1 - 4.4 mm	41 - 177			
4-B		Nu-Klad 127	1	150 - 250	6 - 10	100	High Gloss	Pour and spread Trowell Pour and spread
		Nu-Klad 110C	1	6.25 - 12.5 mm	1/8" - 1/4"	100		
		Nu-Klad 103N	1	250 - 750 mm	10 - 30	100		
			6.65 - 13.5 mm	150 - 290				
5-A	Anti-slip flooring	Amerlock 2/400 with 885 Additive	2	300 - 450	12 - 18	90	Semi-gloss	Roll or Spray
5-B		Amerlock 2/400	1	150 - 200	6 - 8	83	Gloss	Roll or Spray Roll or Spray
		Amershield with 885 Additive	1	125	5	85		
				275 - 325	11 - 13			
5-C		Nu-Klad 127	1	150 - 250	6 - 10	100	High Gloss	Pour and spread Pour and spread Pour and spread
		Nu-Klad 126 Clear with 880 Quartz	1	75 - 150	3 - 6	100		
	Nu-Klad 126 Clear	1	75 - 150	3 - 6	100			
			300- 475	12 - 22				
<b>Secondary Containment</b>								
6	Secondary containment - mild	Amerlock 2/400	3	450 - 600	18 - 24	83	Semi-gloss	Roll or Spray
7-A	Secondary containment - moderate	Amerlock Sealer	1	25 - 50	1 - 2	100	Semi-gloss	Roll or Spray Airless Spray
7-A		Amercoat 351	1	200 - 300	8 - 12	100		
				225 - 375	9 - 14			
7-B		Amerlock Sealer	1	25 - 50	1 - 2	100	Semi-gloss	Roll or Spray Pour and spread
		Nu-Klad 120A		1.0 - 4.375 mm	40 - 175	100		
				1 - 4.4 mm	41 - 177			
7-C		Amercoat 90HS	3	375 - 450	15 - 18	67	Semi-gloss	Roll or Spray
8-A	Secondary containment - severe	Amerlock Sealer	1	25 - 50	1 - 2	100	Matte	Roll or Spray Pour and spread
8-A		PSX 758	1	1 - 1.5 mm	40 - 60	100		
				1 - 1.5 mm +	41 - 62			
8-B		Nu-Klad 127	1	150 - 250	6 - 10	100	High Gloss	Pour and spread Trowell Pour and spread
		Nu-Klad 110C	1	6.25 - 12.5 mm	1/8" - 1/4"	100		
		Nu-Klad 103N	1	250 - 750	10 - 30	100		
			7.0 - 13.5 mm	150 - 280				