

AMERCOAT® 238

April 2013
Revision of October 2012

DESCRIPTION	Reinforced Abrasion Resistant Epoxy
PRINCIPAL CHARACTERISTICS	<ul style="list-style-type: none"> – Outstanding impact and abrasion resistance – Qualified as a high durability deck coating – Suitable for hull exterior for ice-going ships – Low VOC, low HAPs – Excellent low temperature cure – Up to 12 mils dft in one coat
COLOR AND GLOSS	<p>Haze gray, Dark gray, Oxide red, Black Semi-gloss</p> <p><i>* Epoxy coatings will chalk and fade upon exposure to sunlight, elevated temperatures, or chemical exposure. Discoloration and normal chalking does not impact performance. Light colors will darken over time. Some batch-to-batch variation in color is to be expected. Color matches are approximate.</i></p>
BASIC DATA	
Volume solids	77% ± 3%
VOC	1.7 lbs/gal (206 g/L)
Recommended Dry film thickness (per coat)	8 – 12 mils (200-300 microns)
Theoretical Spread Rate	@ 8 mils (5.6 m ² /l) 154 ft ² /gal
Components	2
Shelf Life	3 years from date of manufacture
SURFACE PREPARATION	
Steel	<p>Coating performance is, in general, proportional to the degree of surface preparation.</p> <ul style="list-style-type: none"> – Remove weld spatter, protrusions, and laminations in steel. Grind welds smooth in accordance with NACE RP-0178. Remove all surface contaminants, oil and grease in accordance with SSPC SP-1. <p>Abrasive blast with an angular abrasive to an SSPC SP-10 cleanliness or higher for tank lining service. Achieve a surface profile of 2.0-4.0 mils.</p> <p>For maintenance and repair in atmospheric service, the product can be applied over surfaces prepared in accordance with SSPC SP-11.</p> <p><i>Amercoat 114A may be used as a pit filler for severely pitted steel and surface discontinuities.</i></p> <p>Check with PPG technical service for the maximum allowable soluble salt level for water immersion service. This will vary based on the water chemistry and service temperatures.</p>
Concrete	<ul style="list-style-type: none"> – Prepare / clean surface in accordance with SSPC SP-13 guidelines. Abrade surface per ASTM D-4259 to remove all efflorescence and laitance, to expose sub-surface voids, and to provide a surface roughness equivalent of 60 grit sandpaper or coarser. Test for moisture by conducting a plastic sheet test in accordance with ASTM D4263. Fill voids as necessary with <i>Amercoat 114A</i> epoxy filler.
Non-Ferrous Metals and Stainless Steel	<ul style="list-style-type: none"> – Abrasive blast in accordance with SSPC SP-16 guidelines to achieve a uniform and dense 1.5-4.0 mil anchor profile. Size and hardness of abrasive should be adjusted as necessary based on the hardness of the substrate. Aluminum may be treated with a surface treatment compliant with Mil-DTL-5541 or equivalent (non-immersion applications only).
Aged Coatings and Repairs	<ul style="list-style-type: none"> – Ensure the coating system is sound and well adhered. Do not apply over thermo-plastic coatings or coatings that exhibit poor solvent resistance. A test patch is recommended. Sweep blast or otherwise thoroughly abrade the existing coating in accordance with SSPC SP-7. Alternately, Prep 88 may be used to prepare some existing coatings. Please refer to Prep 88 data sheet for details. Feather the edges of tightly adhered, in-tact coatings at the perimeter of repair areas. Power tool clean the existing steel in accordance with SSPC SP-11 .

AMERCOAT 238

- Aged coatings – All surfaces must be clean, dry, tightly bonded and free of all loose paint, corrosion products or chalky residue. Abrade surface, or clean with Prep 88. *Amercoat 238* is compatible over most types of properly applied and tightly adhering coatings, however, a test patch is recommended to confirm compatibility.
- Repair – Prepare damaged areas to original surface preparation specifications, feathering edges of intact coating. Thoroughly remove dust or abrasive residue before touch-up.

ENVIRONMENTAL CONDITIONS

- Ambient temperatures 32°F to 120°F (0°C to 49°C)
- Material temperatures 40°F to 80°F (5°C to 27°C)
- Relative humidity 0 – 85%
- Surface temperature 32°F to 140°F Surface temperature must be at least 5°F above the dew point temperature.
- General air quality Area should be sheltered from airborne particulates and pollutants. Avoid combustion gases or other sources of carbon dioxide that may promote amine blush. Ensure good ventilation during application and curing. Provide shelter to prevent wind from affecting spray patterns.

INSTRUCTIONS FOR USE

- Mixing ratio by volume 4 parts base to 1 part hardener
Pre-mix pigmented components with a pneumatic air mixing at moderate speeds to homogenize the container. Add hardener to base and agitate with a power mixer for 1-2 minutes until completely dispersed. Strain through 30 mesh.
- Pot life

	50°F	70°F	90°F
Pot life	6 hours	4 hours	2 hours
Induction time	40 minutes	20 minutes	10 minutes
- Airless spray 45:1 pump or larger, (68:1 is most common), 0.025 – 0.031 fluid tip, 2,500 – 4,000 psi, Hardened spray tips and pump internals are recommended as the reinforcement in the product is abrasive.
- Brush & roll Use a high quality natural bristle brush and / or solvent resistant, 3/8" nap roller. Ensure brush / roller is well loaded to avoid air entrainment. Multiple coats may be necessary to achieve adequate film build. Brush/roller application is recommended for minor touch up areas only.
- Thinner *Amercoat T-10 thinner*
- Cleaning solvent 12 Cleaner
- Primers No primer required. Inorganic zinc primers or zinc rich epoxies may be used for severe atmospheric service. Optimum impact resistance is achieved by specifying *Amercoat 238* directly to blasted steel.
- Topcoats *Amercoat 450H, Amershield, PSX 700, Amercoat 229T, PSX One*
- Safety precautions For paint and recommended thinners see safety sheet 1430, 1431 and relevant material safety data sheets
This is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapor as well as contact between the wet paint and exposed skin or eyes.

AMERCOAT 238

DRY/CURE TIMES

Amercoat 238 @ 10 mils dft

	32°F	40°F	50°F	70°F	90°F
Dry hard (hrs)	60	48	24	12	4
Dry through (hrs)	168	72	28	16	12
Dry to recoat / topcoat (hrs)*	38	32	14	6	3.5
Max recoat, epoxy Immersion (days)	21	21	18	12	7
Max topcoat, urethanes, PSX**	7 days	7 days	6 days	4 days	2.5 days
Cure to still water immersion	NR	4 days	2 days	24 hours	18 hours
Cure to light Impact/abrasion***	NR	7 days	4 days	2 days	36 hours
Cure to heavy impact/ abrasion***	NR	28 days	21 days	10 days	5 days

* Antifouling coatings should be applied when the previous coat is tack free, but impressionable with moderate finger tip pressure.

Alkyd coatings and waterborne acrylic coatings should be applied after the film is dry through and no greater than three times the dry through time.

** Dry times are dependent on air and surface temperatures as well as film thickness, ventilation, and relative humidity. Maximum recoating time is highly dependent upon actual surface temperatures – not simply air temperatures. Surface temperatures should be monitored, especially with sun-exposed or otherwise heated surfaces. Higher surface temperatures shorten the maximum recoat window

Surface must be clean and dry. Any contamination must be identified and removed. However, particular attention must be paid to surfaces exposed to sunlight where chalking may be present. In those situations, a further degree of cleaning may be required. PPG Technical Service can advise on suitable cleaning methods. If maximum recoat/topcoat time is exceeded, then roughen surface.

*** Light impact / abrasion is consistent with floating debris or soft bumper impacts. For heavy impact and abrasion resistance, the product can be immersed in accordance with the still water immersion times and allowed to cure underwater for the duration of the times listed for the heavy impact abrasion. The water temperatures should then be referenced. It is recommended that impressed current systems not be activated until the cure for heavy impact/abrasion service is reached.

AVAILABILITY

Packaging	1-gallon and 5-gallon kits	
Product codes	AT238-20	Haze Gray base
	AT238-28	Dark Gray base
	AT238-72	Oxide Red base
	AT238-9	Black base
	AT238-B	Hardener

Worldwide statement

While it is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

WARRANTY STATEMENT

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product.

THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG.

AMERCOAT 238

Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATION OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT.

The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk.

PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product.

Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.
