

AMERCOAT® 385

January 2015
Revision of May 2014

DESCRIPTION	Multi-Purpose Polyamide Epoxy Coating
PRINCIPAL CHARACTERISTICS	<ul style="list-style-type: none"> – Multi-purpose high build epoxy – High solids high build epoxy intermediate coat – Compatibility with a wide range of substrates and surface preparations – <i>Amercoat 385PA</i> contains zinc phosphate for enhanced corrosion inhibitive performance – <i>Amercoat 385LH</i> is formulated for a lower level of HAPs
COLOR AND GLOSS	<p>White, Black, Oxide Red, Buff, Pearl Gray Flat</p> <p><i>Amercoat 385PA Red</i> (MIO containing formula), <i>Amercoat 385PA Buff</i> (no MIO) <i>Amercoat 385LH</i> (Low HAPs Pearl Gray and Solar Red)</p> <p><i>* Epoxy coatings will characteristically chalk and fade upon exposure to sunlight. Light colors are prone to ambering to some extent.</i></p>
BASIC DATA	
Volume solids	68% ± 3%
VOC	2.6 lbs/gal (312 g/L)
Recommended Dry film thickness	3 – 8 mils per coat (75 – 200 microns)
	<i>* For immersion service, the product should be applied at a minimum of 10 mils dft total in 2-3 coats.</i>
Theoretical Spread Rate	<p>@ 1 mil 1090 ft²/gal</p> <p>@ 5 mils 218 ft²/gal</p>
Components	2
Dry Temperature Resistance*	Continuous — 200°F Intermittent — 250°F (<5% of the time, max 24 hours)
	<i>* Color will drift at elevated temperatures.</i>
Shelf Life	3 years from date of manufacture
	<i>* when stored in original sealed containers in dry conditions between 40-100°F</i>
SURFACE PREPARATION	<p>Coating performance is, in general, proportional to the degree of surface preparation. Abrasive blasting is usually the most effective and economical method. When this is impossible or impractical, <i>Amercoat 385</i> can be applied over mechanically cleaned surfaces. All surfaces must be clean, dry and free of all contaminants, including salt deposits. Contact PPG for maximum allowable salt containment levels.</p>
Mild Steel	<ul style="list-style-type: none"> – Remove all loose rust, dirt, grease or other contaminants by one of the following depending on the degree of cleanliness required: SSPC SP-2, 3, 6, 7 or 10 (ISO 8501-1 St-2, St-3, Sa 1, Sa 2.5). These minimum surface preparation standards apply to steel that has been previously abrasive blasted. The choice of surface preparation will depend on the system selected and end-use service conditions. For more severe service and immersion, clean to SSPC SP-10 (ISO8501-1 Sa 2.5). Blast to achieve an anchor profile of 1.0-5.0 mils (50-75microns) as indicted by a Keane-Tator Surface profile Comparator or Testex Tape. For immersion and severe duty applications, the recommended blast profile is 2.0-4.0 mils (50-100 microns). Previously blasted steel may be ultra-high pressure water jetted to SSPC -SP WJ-2(L) / NACE WJ-2(L). The wet surface can be dried by blowing with dry compressed air giving special attention to horizontal surfaces and recesses.
Concrete	<ul style="list-style-type: none"> – Prepare / clean surface in accordance with SSPC SP-13 guidelines. Abrade surface per ASTM D-4259 to remove all efflorescence and laitance, to expose sub-surface voids, and to provide a surface roughness equivalent of 60 grit sandpaper or coarser. Test for moisture by conducting a plastic sheet test in accordance with ASTM D4263. Fill voids as necessary with <i>Amercoat 114A</i> epoxy filler.
Galvanized Steel	<ul style="list-style-type: none"> – Remove oil or soap film with detergent or emulsion cleaner. Lightly abrasive blast with a fine abrasive in accordance with SSPC SP-16 guidelines to achieve a profile of 1.5 - 3.0 mils. When light abrasive blasting is not possible, galvanizing can be treated with a suitable zinc phosphate conversion coating. Galvanizing that has at least 12

AMERCOAT 385

- months of exterior weathering and has a rough surface with white rust present may be over-coated after power washing and cleaning to remove white rust and other contaminants. The surface must have a measurable profile. A test patch is recommended to confirm adhesion. Not recommended over chromate sealed galvanizing without blasting to thoroughly remove chromates. Adhesion problems may occur.
- Non-Ferrous Metals and Stainless Steel
 - Abrasive blast in accordance with SSPC SP-16 guidelines to achieve a uniform and dense 1.5-4.0 mil anchor profile. Size and hardness of abrasive should be adjusted as necessary based on the hardness of the substrate. Aluminum may be treated with a surface treatment compliant with Mil-DTL-5541 or equivalent (non-immersion applications only).
 - Aged coatings
 - All surfaces must be clean, dry, tightly bonded and free of all loose paint, corrosion products or chalky residue. Abrade surface, or clean with Prep 88. *Amercoat 385* is compatible over most types of properly applied and tightly adhering coatings, however, a test patch is recommended to confirm compatibility.
 - Repair
 - Prepare damaged areas to original surface preparation specifications, feathering edges of intact coating. Thoroughly remove dust or abrasive residue before touch-up.

ENVIRONMENTAL CONDITIONS

- Ambient temperatures 40°F to 122°F (5°C to 50°C)
Surface temperature must be at least 5°F above the dew point temperature.
- Material temperatures 50°F to 90°F (10°C to 32°C)
- Relative humidity 85% maximum
- Surface temperature Must be at least 5°F above dew point temperature.
- General air quality Area should be sheltered from airborne particulates and pollutants. Avoid combustion gases or other sources of carbon dioxide that may promote amine blush. Ensure good ventilation during application and curing. Provide shelter to prevent wind from affecting spray patterns.

INSTRUCTIONS FOR USE

- Mixing ratio by volume 1 parts base to 1 part hardener
Pre-mix pigmented components with a pneumatic air mixer at moderate speeds to homogenize the container. Add hardener to base and agitate with a power mixer for 1-2 minutes until completely dispersed.
- Pot life

50°F/10°C	70°F/20°C	90°F/30°C
5 hours	3 hours	1.5 hours
- Induction time

Below 60°F	60-75°F	Above 75°F
30 minutes	15 minutes	Not required
- Airless spray 45:1 pump or larger, 0.017-0.019 fluid tip
Can be applied with plural component equipment
- Air spray Thin up to 20%, standard conventional equipment, 0.070" fluid orifice
- Brush & roll Use a high quality natural bristle brush and / or solvent resistant, 3/8" nap roller. Ensure brush / roller is well loaded to avoid air entrainment. Multiple coats may be necessary to achieve adequate film build.
- Thinner *Amercoat 65* (xylene), *Amercoat T-10*, *Amercoat 101* (recommended for > 90°F)
- Cleaning solvent *Amercoat 12 Cleaner* or *Amercoat 65 thinner* (xylene)
- Primers Direct to substrate; *Dimetcote*- series primers, *Amercoat 68HS*, *Amercoat 68MCZ*
- Topcoats *Amercoat 450-Series Polyurethanes*, *Amershield*, *PSX 700*, *Amercoat 229T*, *PSX ONE*, *Pitthane Polyurethanes*
- Safety precautions For paint and recommended thinners see safety sheet 1430, 1431 and relevant material safety data sheets

AMERCOAT 385

This is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapor as well as contact between the wet paint and exposed skin or eyes.

DRY/CURE TIMES

Amercoat 385 @ 6 mils dft

	40°F	50°F	60°F	70°F	90°F
Dry to touch	8 hours	4 hours	3 hours	2 hours	1 hour
Dry through	96 hours	24 hours	20 hours	16 hours	10 hours
Dry to recoat / topcoat	72 hours	42 hours	24 hours	12 hours	6 hours
Max recoat, self, immersion	30 days or 6 months (when cleaned with Prep 88 according to the instructions)				
Max recoat, self, atmospheric	No maximum (when cleaned with Prep 88 according to the instructions)				
Max topcoat, urethanes, PSX	60 days	42 days	36 days	30 days	14 days
Cure to immersion	10 days	3 days	2.5 days	2 days	1 day

****** Dry times are dependent on air and surface temperatures as well as film thickness, ventilation, and relative humidity. Maximum recoating time is highly dependent upon actual surface temperatures – not simply air temperatures. Surface temperatures should be monitored, especially with sun-exposed or otherwise heated surfaces. Higher surface temperatures shorten the maximum recoat window.

Surface must be clean and dry. Any contamination must be identified and removed. A detergent wash with Prep 88 or equivalent is recommended prior to application of topcoats after 30 days of exposure. However, particular attention must be paid to surfaces exposed to sunlight where chalking may be present. In those situations, a further degree of cleaning may be required. PPG Technical Service can advise on suitable cleaning methods. If maximum recoat/topcoat time is exceeded, then roughen surface

PRODUCT QUALIFICATIONS

- Mil-PRF-23236(C) Type V, Class 7, Grade C
- Military Sealift Command – Underwater hulls, topside and salt water ballast tank service
- Compliant with USDA Incidental Food Contact Requirements
- NFPA Class A for Flame Spread and Smoke Development
- AWWA C210-98
- NORSOK M501 Rev. 5, System 7 Subsea surfaces
- MPI Category #108

AVAILABILITY

Packaging

Available in 2-gallon and 10-gallon kits
 2-gallon kits have 1 full gallon of base and 1 full gallon of hardener
 10-gallon kits have 5-gallons of base and 5-gallons of hardener

Inventory

Global availability

Product codes

AT 385-1	Buff base
AT 385-3	White base
AT 385-9	Black base
AT 385-23	Pearl Gray base
AT 385-72	Oxide Red base
AT385A-1	Amercoat 385PA Buff (contains zinc phosphate)
AT385A-7	Amercoat 385PA Red (contains micaceous iron oxide)
AT385LH23	Amercoat 385LH (Low HAPs Pearl Gray)
AT385LH702	Amercoat 385LH (Low HAPs Solar Red)
AT385-B	Hardener component (hardener for 385 and 385PA)
AT385LH-B	Low HAPs Hardener component

Worldwide statement

While it is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

AMERCOAT 385

WARRANTY STATEMENT

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product.

THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG.

Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATION OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT.

The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk.

PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product.

Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.
