

# PSX<sup>®</sup> ONE

August 2013  
Revision of October 2012

<b>DESCRIPTION</b>	High Solids, Single Pack Acrylic Polysiloxane
<b>PRINCIPAL CHARACTERISTICS</b>	<ul style="list-style-type: none"> <li>- High gloss topcoat</li> <li>- High solids, low VOC</li> <li>- Ease of application, brush, roll, or spray</li> <li>- Isocyanate free</li> <li>- Excellent gloss retention</li> <li>- Meets SSPC Paint 36 Level 3 requirements</li> </ul>
<b>COLOR AND GLOSS</b>	<p>Standard Color Offering, Safety Colors, Custom Colors</p> <p>Gloss</p> <p><i>* Certain colors, especially red, orange, and yellow may require additional coats for adequate hiding, especially if applied over primers with a significant color contrast.</i></p>
<b>BASIC DATA</b>	
Volume solids	75% ± 3%
VOC	1.75 lbs/gal (210 g/L)
Recommended Dry film thickness (per coat)	2 – 3 mils (50 – 75 microns)
Theoretical Spread Rate	<p>@ 1 mil dft    1203 ft<sup>2</sup> / gallon</p> <p>@ 2 mils dft   602 ft<sup>2</sup> / gallon</p> <p>@ 3 mils dft   401 ft<sup>2</sup>/ gallon</p>
Components	1
Shelf Life	6 months from date of manufacture
<b>SURFACE PREPARATION</b>	<p>Coating performance is proportional to the degree of surface preparation. Refer to the application instructions for specific primers and intermediate coats for application and curing procedures. Ensure epoxies are free from amine blush prior to overcoating. All previous coats must dry and free of contaminants. Adhere to all minimum and maximum topcoat times for specific primers and intermediate coats. Aged epoxy coatings may require abrading prior to applying <i>PSX ONE</i>. A test patch over unknown coatings is recommended.</p>
<b>ENVIRONMENTAL CONDITIONS</b>	
Ambient temperatures	40°F to 120°F (5°C to 49°C)
Material temperatures	50°F to 90°F (10°C to 32°C)
Relative humidity	20 – 90%
Surface temperature	40°F to 120°F (5°C to 49°C) Surface temperature must be at least 5°F above dew point temperature.
General air quality	Area should be sheltered from airborne particulates and pollutants. Avoid combustion gases or other sources of carbon dioxide that may promote ambering of light colors. Ensure good ventilation during application and curing. Provide shelter to prevent wind from affecting spray patterns.
<b>INSTRUCTIONS FOR USE</b>	
Mixing	Agitate with a power mixer for 1-2 minutes until completely dispersed.
Airless spray	30:1 pump or larger, 0.013 - 0.017 fluid tip
Air spray	Thin up to 20%, standard conventional equipment, 0.070" fluid orifice. A moisture and oil trap in the main line is essential.
Brush & roll	Use a high quality natural bristle brush and / or solvent resistant, 1/4" or 3/8" nap roller. Ensure brush / roller is well loaded to avoid air entrainment. Multiple coats may be necessary to achieve adequate film build. <i>Amercoat 851</i> flow control additive can be used to for enhanced flow and leveling with brush and roll application.

## PSX ONE

Thinner	<i>Amercoat 911</i>
Cleaning solvent	<i>Amercoat 12 Cleaner or Amercoat 911 thinner</i>
Primers	<i>Amercoat One, Amercoat 5105, Amercoat 185H, Amercoat 370, Amercoat 385, Amercoat 399, Amerlock 2/400, Amercoat 235, Amercoat 240, Pittguard Epoxies, Amerlock Sealer, Amercoat 68HS, Amercoat 237M</i>
Safety precautions	For paint and recommended thinners see safety sheet 1430, 1431 and relevant material safety data sheets  This is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapor as well as contact between the wet paint and exposed skin or eyes.

### DRY/CURE TIMES

PSX ONE @ 2 mils dft

	50°F	70°F	90°F
Dry to touch	3 hours	2 hours	1 hour
Dry through	16 hours	9 hours	5 hours
Dry to recoat	5 hours	2 hours	1 hour
Maximum recoat	30 days		

### AVAILABILITY

Packaging	Available in 1-gallon and 5-gallon units
Product codes	PXONE23 Pearl Gray base PXONE3 White base PXONE9 Black base PXONET1 Deep tint base* PXONET2 Light tint base* PXONET3 Neutral tint base* PXONET4 Red tint base* PXONET5 High Hiding Yellow tint*

\* Tintable with UCD PS Line colorants only.

Worldwide statement	While it is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.
---------------------	--

### WARRANTY STATEMENT

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product.

THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG.

Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## PSX ONE

---

### **LIMITATION OF LIABILITY**

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT.

The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk.

PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product.

Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

---